



.....

**Material Datasheet:**  
**CuZn39Pb1Al-B**  
**(CB754S)**

.....

**BRASS INGOTS**

# CB754S

**Standard  
base alloy  
with wide  
application**

**CB754S is the base material for the sanitary industry, when the demand of a material with good properties is needed. The properties of this alloy allow a large application on water related products, since sanitary ware to fittings, valves or connectors.**

## MATERIAL DESIGNATION

ASBW	International	EN	UNS	JIS	Further Restrictions
L06	CuZn39Pb1Al-B	CB754S (CC754S)**	-	-	-

## REFERENCE CHEMICAL COMPOSITION IN % (MAIN ELEMENTS) \*


Material**	Cu	Pb	Ni	Fe	As	Sn	Al	Bi	Zn
L06*	58,8	2,0	0,3	0,7	-	0,3	0,6	-	Remainder

\* Deviations from these values may occur within the restrictions of the relevant standard specifications. Elements not listed are complying with EN1982.

\*\* The material symbol designation is based on the designation system given in ISO 1190-1. A "CB" is added to the designation to identify material in the form of ingots and a "CC" is added to the designation to identify material in the form of castings. These distinctions serve to avoid confusion with wrought products of a similar alloy.

## TYPICAL MICROSTRUCTURE

- L06 ( $\alpha$ -phase brighter +  $\beta$ -phase darker):



## FABRICATION PROPERTIES

### FORMING

Machinability (CuZn39Pb3 = 100 %)	85%
Castability	Excellent

### JOINING

Resistance Welding (Butt Welding)	Fair
Inert Gas Shielded Arc Welding	Poor
Gas Welding (Most Commonly Oxyacetylene)	Not Recommended
Hard Soldering	Fair
Soft Soldering	Good
Brazing	Good

### POLISHING

Mechanical	Reasonable
------------	------------

## WORK TEMPERATURE/HEAT TREATMENT

Smelting Range	900 - 1020 °C
----------------	---------------

## PRODUCT STANDARDS

Ingot	EN 1982
-------	---------

## CORROSION RESISTANCE

Machining brass is quite resistant to organic substances and to neutral or alkaline compounds. In comparison, homogeneous  $\alpha$ -brass has a much more satisfactory corrosion resistance due to its microstructure. As for the stress corrosion cracking and dezincification, specially under conditions as warm, acidic waters and ammoniacal atmospheres, they should be taken into consideration, even more when the material is not under a stress relieved condition.

## Physical properties\*

Material Density [g/cm <sup>3</sup> ]	Electrical Conductivity		Thermal Conductivity [W/(m.K)]	Thermal Expansion Coefficient (0 - 300 °C) [10 <sup>-6</sup> /K]	Modulus of Elasticity [GPa]
	[MS/m]	[% IACS]			
8,44	14,38	24	111	20,3	114

\* Reference values at room temperature

## Mechanical properties

acc. to EN 1982

Alloy	Casting process and designation	Tensile strength	0,2 % Proof strength	Elongation	Hardness
		Rm	Rp0.2	A	HB
		MPa min.	MPa min.	[%] min.	min.
CB754S/CC754S	Sand -GS	220	80	15	65
	Permanent mould - GM	280	120	10	70
	Pressure die cast - GP	350	250	3	110
	Centrifugal - GZ	280	120	10	70

## FINISHING AND PACKAGING

Pallet numbering	<b>Identified in the label attached to each pallet</b>
Sampling	<b>Possibility of shipment of the brass ingot with one polished sample either per pallet or per melting charge with the respective microstructure picture, upon customer's request and agreement.</b>
Packaging	<b>The ASBW brass ingots are shipped in wooden euro pallets. There standard type of pallet building configuration and weight is three complete rows of ingots, with a total weight between 1100 and 1200 Kg Each pallet is protected with a polymeric net all around and steel strapped five times to ensure a secure shipment and material integrity during the transportation. Different packaging weights and row configuration possible upon customers request and agreement.</b>
Identification	<b>Adhesive label on bundle strap:</b> <ul style="list-style-type: none"><li>- Customer</li><li>- Number of customer's order</li><li>- EN Standard of the material</li><li>- Alloy identification (International and EN)</li><li>- ASBW material code and LOT number ensuring production tracking</li><li>- Ingot dimensions</li><li>- ASBW's PO number</li><li>- ASBW's Quality Approval Seal</li></ul>

The technical information within this datasheet is provided by **ASBW** without any surcharge.  
The end use of this content is up to the user discretion and risk.  
For further detailing on technical aspects such as material condition, machining, mechanical data, temper  
selection through contact to our technical personal.



**BARBOSA WORLD BRASS, S.A**

Main office and factory: Rua de Sousanil, 476, 4525-100 Canedo VFR, Santa Maria da Feira - Portugal  
Phone: +351 227 637 040  
Email: [asbw@asbw.pt](mailto:asbw@asbw.pt)  
NIPC: 515 557 552  
Social Capital: € 350.000